TECHNICAL DATA SHEET



K-LITE 875



K-LITE range 875 adhesive is a photosensitive epoxybased hybrid resin developed especially for doming applications. Thanks to its innovative formulation, 875 glue combines the advantages of epoxy resins and UV systems, offering superior adhesion, a high-quality visual finish and excellent resistance to humidity.

SINGLE COMPONE TRANSPARENT DRY SURFACE MOISTURE RESISTA		
HIGH: TEMPERATUR		
CHEMICAL BASIS	Epoxy Acrylate	
HARDENING MODE	UV	
CURING TIME	30s	
COLOR	Transparent	

PROPERTIES	875		
Chemical base	Epoxy acrylate		
Viscosity @23°C 6 RPM, S4 Brookfield mobile (mPa.s)	70,000		
Appearance	Viscous		
Color	Transparent		
Surface condition (polymerized resin)	Dry surface		
Absorption wavelength	300 - 365nm		
Breaking force(ISO 527-1) (MPa) VM,60 seconds	30		
Elongation at break(ISO 527-1) VM,60 seconds - %	7		
Shear strength(MPa) Compression-shear – VM, 30 seconds	Glass	3	
	PC	3	
	PMMA	3	
	DC04 Steel	3.5	
Shore D hardness	90 +/-5		
Transmission rate %	98.7		
Water absorption (% m/m)	0.8		
Thixotropy index	9.6		
Temperature range of use (°C)	-25 to +150°C		
Shelf life in packaging	6 months		
Complete polymerization (hour)	24		

LE K DES COLLES!

KEOL

SURFACE PREPARATION

The strength and durability of joints depends on proper pretreatment of the surfaces to be bonded. At a minimum, the bonded surfaces should be cleaned with a good degreasing product to remove all traces of dust, dirt, oils or grease. KEOL CLEANER is particularly recommended for cleaning surfaces before bonding.

Pretreatment of thermoplastic materials such as PVC, polycarbonate, polypropylene, PMMA, etc., can be done using a mild mixture of ethers or isopropanol. It is not recommended to use strong solvents as they may damage plastic surfaces.

For any other surface, acetone or trichloroethylene can be used for pretreatment. Never use petroleum or any other solvent.

When possible, perform mechanical abrasion to remove paint from surfaces (if necessary) and to increase the strength and retention of the adhesive. Allow the pre-treated surface to dry before applying the adhesive.

PACKAGING

K-LITE range 875 adhesive is available in 30 and 600cc syringes, 1L, 3.5L pots and 20L drums.

PRODUCT STORAGE

Shelf life of **875 adhesive** is 6 months in its original unopened packaging. The product can be stored in a closed container, in a dry place protected from humidity and excessive heat. Storage between 15°C and 25°C. Exposure to higher or lower temperatures will result in a reduction of the indicated shelf life, as well as possible loss of performance.

PRECAUTIONS FOR HANDLING THE PRODUCT

precautions K-I ITF products generally safe handle, provided that regarding are to handling of chemicals are taken. The cartridge product should not come into contact with food products or cooking utensils, and certain safety measures should be taken to prevent the contents of the cartridges from escaping and coming into contact with the skin, as people with very sensitive skin may be affected. The use of rubber or plastic gloves is recommended, as is eye protection. The skin should be thoroughly cleaned at the end of each work session by washing with soap and warm water. Avoid the use of solvents. To dry the skin, use disposable paper. Adequate ventilation for the work area is recommended. These precautions are explained in more detail in the safety data sheet for the individual products and you should refer to this document for further information.

ΝΟΤΕ

The information, and particularly the recommendations concerning the application and KEOL products, are given to you in good faith and are based on current knowledge and experience of the products having been properly stored, handled and applied under normal conditions. KEOL cannot assume responsibility for the results obtained by others since we have no control over their method. It is up to the user to determine the suitability of the products for the specific application for any production methods mentioned in this document. Also, it is up to the user to adopt the necessary precautions as advised for the products. KEOL cannot assume any warranties mentioned or implied, including warranties of merchantability or fitness for a particular reason, arising from the sales or use of KEOL products. KEOL cannot assume responsibility for incidental or consequential damages of any kind, including lost profits. Users should always refer to the most recent edition of the technical data sheet for the relevant product. Copies of this document will be provided on request.

LE K DES COLLES!